



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification 7 : <b>D04H 3/16</b>		<b>A1</b>	(11) International Publication Number: <b>WO 00/66824</b>
			(43) International Publication Date: 9 November 2000 (09.11.00)
(21) International Application Number: <b>PCT/US00/10759</b>		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 21 April 2000 (21.04.00)			
(30) Priority Data: 60/132,031 30 April 1999 (30.04.99) US 09/537,564 30 March 2000 (30.03.00) US			
(71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 North Lake Street, Neenah, WI 54956 (US).			
(72) Inventors: NEELY, James, Richard; 3585 Waters Cove Way, Alpharetta, GA 30202 (US). WHITE, Edward, Jason; 12206 Aroniminik Point, Knoxville, TN 37922 (US). BROWN, Kurtis, Lee; 700 Rhodes Creek Trail, Alpharetta, GA 30004 (US). CONRAD, John, Herbert; 625 Briars Bend, Alpharetta, GA 30004 (US). HOEFER, Richard, Wallace; 8048 West Arapaho Court, Boise, ID 83703 (US).			
(74) Agents: NORRIS, Roland, W.; Pauley Petersen Kinne & Fejer, Suite 365, 2800 West Higgins Road, Hoffman Estates, IL 60195 (US) et al.			

**Published***With international search report.**Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.*

(54) Title: CONTROLLED LOFT AND DENSITY NONWOVEN WEBS AND METHOD FOR PRODUCING

## (57) Abstract

A lofty, nonwoven material having a nonwoven web having a plurality of substantially continuous fibers oriented in a z-direction of the nonwoven web and a method for producing the lofty, nonwoven material from as-formed z-direction fibers. The method is fast, having no mechanical manipulation of the fibers to slow it down, easily adjustable and allows for in-line processing. The material can be varied from preponderantly open to preponderantly closed in its web structure.



*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

# CONTROLLED LOFT AND DENSITY NONWOVEN WEBS AND METHOD FOR PRODUCING

## BACKGROUND OF THE INVENTION

### Field of the Invention

This invention relates to a lofty, nonwoven material produced from continuous fibers in which the lofty character of the nonwoven material is the result of the fibers comprising the web being oriented in a z-direction, that is outside of the plane of the orientation of the web, of the nonwoven material. These materials are particularly suitable for use in a broad range of applications including fluid management (surge), air and liquid filtration, acoustic and thermal insulation, packing material, absorbents, and cleaning materials. More particularly, these materials are suitable for use as surge, spacer layers, filtration materials and absorbent layers in personal care absorbent products including disposable diapers, incontinence garments, and feminine care products such as sanitary pads and napkins, and in face masks, surgical gowns, sterile wraps and surgical drapes. In addition, this invention relates to methods for producing such lofty, nonwoven materials.

### DISCUSSION OF RELATED ART

Absorbent personal care articles such as sanitary pads and napkins, disposable diapers, incontinent-care pads and the like are widely used, and much effort has been made to improve their effectiveness and functionality. These articles generally include a liquid absorbent material backed by a liquid-impervious barrier sheet. To enhance the sense of comfort, the absorbent material has a facing of a material which masks at least the body-facing surface of the product. The purpose of this cover material is to help structurally contain the absorbent material and to protect the wearer from continuous direct contact with moisture from previously wetted absorbent material. The cover material is typically of relatively low basis weight nonwoven fabric. Improved product performance has been obtained in these products through the incorporation of a surge management material disposed between the cover material and the absorbent material. The surge management material is made from a relatively high basis weight, low density, that is, thick, nonwoven web material.

In nonwoven webs, the fibers comprising the web are generally oriented in the x-y plane of the web and the resulting nonwoven web material is relatively thin, that is lacking in loft or significant thickness. Loft or thickness in a nonwoven web suitable for use in personal care absorbent articles promotes comfort (softness) to the user, surge management and fluid distribution to adjacent layers.

In order to impart loft or thickness to a nonwoven web, it is generally desirable that at least a portion of the fibers comprising the web be oriented in the z-direction. Conventionally, such lofty nonwoven webs are produced using staple fibers. See, for example, U.S. Patent 4,837,067 which teaches a nonwoven thermal insulating batt comprising structural staple fibers and bonding staple fibers which are entangled and substantially parallel to the faces of the batt at the face portions and substantially perpendicular to the faces of the batt, and U.S. Patent 4,590,114 which teaches a batt including a major percent of thermo-mechanical wood pulp fibers stabilized by the inclusion of a minor percent of thermoplastic fibers including staple length thermoplastic fibers. Alternatively, conventional high loft forming processes rely on pre-forming processes such as fiber crimp formed on a flat wire or drum, and post-forming processes such as creping or pleating of the formed web.

#### SUMMARY OF THE INVENTION

In contradistinction to the known art, the present invention does not first form a web of material and pleat it. Rather, fibers are looped, or bent, on themselves without being first being formed into a material web. These fiber level loops, running between the major surfaces of the resultant web, are aggregated in the cross machine direction to form structures running in the cross machine direction which are herein sometimes called "waves" or "folds" to distinguish them from "pleats" which refer to structures in preformed web or mesh material that has been folded on itself.

Accordingly, it is one object of this invention to provide a high loft, low density nonwoven web material comprising substantially continuous fibers as opposed to staple fibers traditionally used in the manufacture of such nonwoven materials.

This and other objects of this invention are addressed by a lofty, nonwoven material comprising a nonwoven web comprising a plurality of substantially continuous

fibers, which may be crimped or linear, oriented in a z-direction of the nonwoven web. The substantially continuous fibers are preferably spunbond and/or meltblown. In accordance with one embodiment of this invention, a support structure may be attached to at least one face of the nonwoven web, thereby providing strength to the high loft nonwoven web. This  
5 laminate structure provides support for the high loft structure, strength for winding, converting, etc., and a boundary layer to either enhance or retard fluid flow into the lofty absorbent structure in products such as disposable diapers, incontinence garments, and absorbent feminine care products including sanitary pads and napkins.

The lofty, nonwoven material of this invention is produced in accordance with  
10 one embodiment of this invention by a process in which a plurality of substantially continuous fibers are directed into a variable nip, resulting in bending of the fibers and formation of a nonwoven web. Within the nip the fibers may be subjected to a vacuum from both sides of the nip, either equally or differentially, producing a lofty, nonwoven web having a plurality of the substantially continuous fibers oriented in a z-direction.

15 In accordance with another embodiment of this invention, the lofty, nonwoven material is produced by directing a plurality of continuous, substantially linear, filament fibers through a slot formed by two opposed surfaces whereby the substantially continuous fibers bend from contact with the two opposed surfaces, which may be differential speeds or vacuum, or both, thereby forming a lofty, nonwoven web having a plurality of as-formed  
20 z-direction fibers.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects and features of this invention will be better understood from the following detailed description taken in conjunction with the drawings wherein:

25 Fig. 1 is a diagram of a process for producing a lofty, nonwoven material in accordance with one embodiment of this invention;

Fig. 2 is a diagram of another process for producing a lofty, nonwoven material in accordance with another embodiment of this invention;

Figs. 3A and 3B are diagrammatic representations of a conventional nonwoven web and a high loft nonwoven web in accordance with this invention, respectively;

Fig. 4 is a photograph of a side view of a high loft nonwoven web produced in accordance with the method of this invention;

5 Figs. 5-7 illustrate a material made according to the method of Fig. 2 with equal speed on the opposing surfaces; and

Figs. 8-10 illustrate a material made according to the method of Fig. 2 with differential speed on the opposing surfaces.

10

## DETAILED DESCRIPTION OF THE PRESENTLY PREFERRED EMBODIMENTS

### DEFINITIONS

As used herein, the term "nonwoven web" or "nonwoven material" means a web having a structure of individual fibers, filaments or threads which are interlaid, but not in a regular or identifiable manner, such as in a knitted fabric and films that have been fibrillated. Nonwoven webs or materials have been formed from many processes such as, for example, meltblowing processes, spunbonding processes, and bonded carded web processes. The basis weight of nonwoven webs or materials is usually expressed in ounces of material per square yard (osy) or grams per square meter (gsm), and the fiber diameters usable are usually expressed in microns. (Note that to convert from osy to gsm, multiply osy by 33.91.)

As used herein, the term "z-direction" refers to fibers disposed outside of the plane of orientation of a web. Fig. 3A is a diagram showing a nonwoven web without z-direction fibers. That is, all of the fibers are generally oriented in the direction indicated by arrow 27. By comparison, Fig. 3B is a diagram showing a nonwoven web having z-direction fibers in accordance with this invention. That is, in addition to fibers oriented in the direction of arrow 28, fibers are also oriented in the direction of arrows 29 and 30. The term "as formed z-direction fibers" as used herein refers to fibers that become oriented in the z-direction during forming of the nonwoven web as distinguished from fibers having a z-direction component resulting from post-forming processing of the nonwoven web, such as in the case of mechanically crimped or creped nonwoven webs.

As used herein, the term "spunbond fibers" refers to small diameter fibers which are formed by extruding molten thermoplastic material as filaments from a plurality of fine, usually circular capillaries of a spinneret as taught, for example, by U.S. Patent 4,340,563 to Appel et al. and U.S. Patent 3,802,817 to Matsuki et al.

5 As used herein, the term "meltblown fibers" refers to fibers formed by extruding a molten thermoplastic material through a plurality of fine, usually circular, die capillaries as molten threads or filaments into converging high velocity gas streams (for example, airstreams) which attenuate the filaments of molten thermoplastic material to reduce their diameter, which may be to microfiber diameter. Such a process is disclosed, for  
10 example, by U.S. Patent 3,849,241 to Butin.

As used herein, the term "microfibers" refers to small diameter fibers having an average diameter not greater than about 75 microns, for example, having an average diameter of from about 0.5 microns to about 50 microns, or more particularly, having an average diameter of from about 2 microns to about 40 microns.

15 As used herein, the term "polymer" generally includes, but is not limited to, homopolymers, copolymers, such as, for example, block, graft, random and alternating copolymers, terpolymers, etc., and blends and modifications thereof. Furthermore, unless otherwise specifically limited, the term "polymer" also includes all possible geometric configurations of the material. These configurations include, but are not limited to, isotactic,  
20 syndiotactic, atactic and random symmetries.

As used herein, the term "personal care absorbent article" means disposable diapers, training pants, absorbent underpants, adult incontinence products, feminine hygiene products and the like.

As used herein, the term "homofilament" refers to a fiber formed from only  
25 one polymer. This is not meant to exclude fibers formed from one polymer to which small amounts of additives have been added for coloration, anti-static properties, lubrication, hydrophilicity, etc.

As used herein, the term "bicomponent fibers" refers to fibers which have been formed from at least two polymers extruded from separate extruders but spun together  
30 to form one fiber. Bicomponent fibers are also sometimes referred to as conjugate fibers or

multicomponent fibers. Bicomponent fibers are taught by U.S. Patent 5,382,400 to Pike et al.

As used herein, the term "biconstituent fibers" refers to fibers which have been formed from at least two polymers extruded from the same extruder as a blend. The  
5 term "blend" is defined below. Biconstituent fibers are sometimes also referred to as multiconstituent fibers. Fibers of this general type are discussed in, for example, U.S. Patent 5,108,827 to Gessner. As used herein, the term "blend" means a mixture of two or more polymers.

As used herein, the term "substantially continuous fibers" refers to fibers,  
10 including without limitation, spunbond and meltblown fibers, which are not cut from their original length prior to being formed into a nonwoven web or fabric. Substantially continuous fibers may have average lengths ranging from greater than about 15 centimeters to more than one meter, and up to the length of the web or fabric being formed. The definition of "substantially continuous fibers" includes fibers which are not cut prior to being  
15 formed into a nonwoven web or fabric, but which are later cut when the nonwoven web or fabric is cut, and fibers which are substantially linear or crimped.

The term "staple fibers" means fibers which are natural or cut from a manufactured filament prior to forming into a web, and which have an average length ranging from about 0.1-15 centimeters, more commonly about 0.2-7 centimeters.

As used herein, the term "through-air bonding" or "TAB" means the process  
20 of bonding a nonwoven, for example, a bicomponent fiber web in which air which is sufficiently hot to melt one of the polymers of which the fibers of the web are made is forced through the web.

Potential applications for the nonwoven web of this invention include  
25 personal care absorbent articles such as diapers, training pants, incontinence garments, feminine care products including sanitary pads and napkins, all surge materials, loop for hook and loop, air filtration, liquid filtration, body scrub pads, oil sorb, baby wipes, industrial wipes, insulation and packaging material. In the case of filtration materials, the method of this invention greatly increases the surface area and volume available for filtration. In  
30 addition, the method of this invention may be suitable for producing coforms or composite materials incorporating high loft surge/pulp/superabsorbent material. And, for a continuous



roll of diapers, a composite material made by the present invention could be produced by ridging or ruffling a high loft surge/pulp/superabsorbent material laminate and placing it in between an outer cover and a liner, which would produce a laminate with all of the components of a diaper in a single step, which could be wound up and cut and placed later on converting machines.

The lofty or high loft nonwoven material of this invention comprises a nonwoven web comprising a plurality of substantially continuous fibers oriented in a z-direction of the nonwoven web. The substantially continuous fibers preferably are drawn in spunbond or meltblown processes. The substantially continuous fibers are preferably formed with polymers selected from the group consisting of polyolefins, polyamides, polyesters, polycarbonates, polystyrenes, thermoplastic elastomers, fluoropolymers, vinyl polymers, and blends and copolymers thereof. Suitable polyolefins include, but are not limited to, polyethylene, polypropylene, polybutylene, and the like; suitable polyamides include, but are not limited to, nylon 6, nylon 6/6, nylon 10, nylon 12 and the like; and suitable polyesters include, but are not limited to, polyethylene terephthalate, polybutylene terephthalate, polytrimethyl terephthalate, polylactic acid and the like. Particularly suitable polymers for use in the present invention are polyolefins including polyethylene, for example, linear low density polyethylene, low density polyethylene, medium density polyethylene, high density polyethylene and blends thereof; polypropylene; polybutylene and copolymers as well as blends thereof. Additionally, the suitable fiber forming polymers may have thermoplastic elastomers blended therein.

In accordance with one preferred embodiment of this invention, the substantially continuous fibers are bicomponent fibers. Particularly suitable polymers for forming the structural component of suitable bicomponent fibers include polypropylene and copolymers of polypropylene and ethylene, and particularly suitable polymers for the adhesive component of the bicomponent fibers includes polyethylene, more particularly linear low density polyethylene, and high density polyethylene. In addition, the adhesive component may contain additives for enhancing the crimpability and/or lowering the bonding temperature of the fibers, and enhancing the abrasion resistance, strength and softness of the resulting webs. The nonwoven web of the material of this invention has a basis weight in the range of about 0.25 osy to about 50 osy. To enhance the absorption characteristics of the

nonwoven material, in accordance with one embodiment of this invention, the nonwoven web comprises an absorbent, for example, superabsorbent particles as a coform.

In accordance with one embodiment of this invention, a support structure is attached to at least one face of the nonwoven web so as to provide strength thereto. The resulting laminate structure provides support for the high loft structure, strength for winding, converting, etc., and a boundary layer to either enhance or retard fluid flow into the lofty absorbent structure. The support structure may include spunbond webs of various types including liners, perforated, micro-fiber, creped, etc., spunbond-meltblown-spunbond (SMS), meltblown, and/or films.

As used herein, the term "coform" means a process in which at least one meltblown diehead is arranged near a chute through which other materials are added to the web while it is forming. Such other materials may be pulp, superabsorbent particles, cellulose or staple fibers, for example. Coform processes are shown in commonly assigned U.S. Patent 4,818,464 to Lau.

In a method for producing a lofty, nonwoven material in accordance with one embodiment of this invention, Fig. 1, a plurality of substantially continuous fibers are conveyed into a variable nip 19, that is a nip in which one of the elements forming the nip is adjustable, thereby enabling adjustment of the size of the nip in which the fibers are subjected to a vacuum from both sides of the nip, resulting in a lofty, nonwoven web having a plurality of the substantially continuous fibers oriented in a z-direction. Such a lofty, nonwoven web is shown in Fig. 4 in which the individual fibers comprising the web can be seen.

In accordance with the embodiment shown in Fig. 1, a plurality of substantially continuous fibers 14 are generated by a fiber forming unit 11 and are deflected by deflector 12 directly into a variable nip 19 formed by drum former 16 and forming surface 18. In accordance with the embodiment shown, the nip is varied by vertically adjusting drum former 16. Varying the nip in this fashion allows control over the density and loft of the nonwoven web. Within drum former 16 disposed above the nonwoven web, forming box 15 disposed below the forming surface 18, are means for subjecting the substantially continuous fibers 14 to a vacuum as the web passes through variable nip 19. The nonwoven web is thus formed in the variable nip 19, as opposed to upstream of the nip on a forming

surface, is a high loft nonwoven web. Loft in the nonwoven web as it passes through the variable nip can be maintained by application of the vacuum to both sides of the web. In accordance with one embodiment of this invention, the resulting lofty, nonwoven web is subjected to treatment by a hot air knife 17 for the purpose of increasing the integrity of the nonwoven web. A hot air knife is used to bond the individual polymer fibers together at various locations so that the web has increased strength and structural integrity for subsequent treatments such as passage through a through-air bonding unit. A conventional hot air knife includes a mandrel with a slot that blows a jet of hot air onto the nonwoven web surface. Such hot air knives are taught, for example, by U.S. Patent 5,707,468 to Arnold et al. Alternatively, the nonwoven web may be set by an adhesive sprayed onto the fibers prior to entering variable nip 19 by adhesive system 13, or by a combination thereof, e.g., a thermally activated adhesive.

Although shown as a combination of drum former 16 and forming surface 18, it will be apparent to those skilled in the art that variable nip 19 may be formed by other means, such as two drum formers, two opposed moving belts, etc.

In order to vary the 3-dimensional structure of the nonwoven web for a given fiber, the relative speeds of the drum former 16 and moving forming surface 18, as well as the height of the nip, and amount of vacuum may be varied. In accordance with one preferred embodiment of this invention, the speed of rotation of drum former 16 corresponds to the speed at which moving forming surface 18 is traveling. In accordance with another preferred embodiment of this invention, the speed at which drum former 16 is rotating is different from the speed of travel of moving forming surface 18. After forming in variable nip 19, the nonwoven web is integrally fixed, i.e., its structure is set by a hot air knife, adhesive, a calender, through-air-bonding unit, or the like and without laminate additions.

In accordance with one preferred embodiment of this invention, laminate structures are produced by unwinding and/or alternately producing and introducing one or more fabrics to be formed upon the web of the present invention. By either unwinding onto drum former 16 and/or web forming surface 18, applying adhesive in one or more possible places, and forming the lofty, nonwoven web as described hereinabove, a multi-layer laminate structure can be produced.

Fig. 2 is a diagram showing an alternative method for producing a lofty, nonwoven material in accordance with this invention. In the embodiment shown in Fig. 2, substantially continuous fibers 14 are directed in a first direction, in this instance vertically downward, through slot 35 formed by two opposed surfaces, such as foraminous or perforate, forming wires 32, 33, whereby the substantially continuous fibers bend from contact with the two opposed surfaces, forming a lofty, nonwoven web having a plurality of as-formed z-direction fibers. After passing through slot 35, the resulting lofty, nonwoven web may be passed through a calender unit or some other downstream apparatus such as a through-air bonder for further processing. Alternatively, as shown in Fig. 2, where slot 35 is formed by the two foraminous wires 32, 33, the high loft nonwoven web may be subjected to through-air bonding, as at arrow 36, as the web passes through slot 35, thereby enabling the web to be formed in a single step.

The loft and density of the nonwoven web produced in accordance with the method of this invention is defined in part by the distance between the two opposed surfaces 32, 33. The density of the nonwoven web may be controlled by adjustment of the speed at which the nonwoven web passes through slot 35 and/or by varying the width of slot 35. Slot 35 may be a fixed plate slot, but the dual wire system shown in Fig. 2 is considered to be a more efficient method of web forming. Typically, adjustment of the distance between opposed surfaces forming the nip or slot, the speed at which the material passes through the nip or slot, and the relative speed of the moving surfaces forming the nip or slot and amount and direction of applied vacuum, are necessary to produce a nonwoven web with given characteristics. The forming nip or slot may also have parallel, or converging, or a series of converging and expanding slots. Adjustment of any or all of these factors may result in great variations of web characteristics.

As stated above, spunbond and meltblown fibers can be used to produce the high loft nonwoven web of this invention. Single component (homofilament), bicomponent and biconstituent fibers can be used. Bicomponent fibers are preferred in accordance with one embodiment of this invention because they have the advantage that thermal bonding fiber crimp can be used to enhance lofty material properties. The fibers can also be either quenched (rapidly cooled), in which case the outer surface of the fibers is solidified, or unquenched in which case the outer surface of the fibers remains tacky. Unquenched fibers

have the advantage of bonding to each other without a further bonding requirement. Thermoplastic fibers can be through-air bonded in a stuffed through-air bonder unit symbolically shown as arrow 36 in Fig. 2, thereby providing a one-step forming/bonding process. Other types of bonding, such as bonding rolls, may be placed after the stuffed  
5 through-air-bonder unit for material consolidation, including point-bonding, hydro-entangling, or needle punching.

Referencing Figs. 4-7 a nonwoven material 40 made according to the method of Fig. 2 has first and second major surfaces 42, 44 in the plane of the web, i.e., generally parallel to the XY plane, and spaced apart in the Z direction. The continuous fibers, e.g., 46,  
10 are folded to form loops, e.g., 48, whose z-direction termini are fused into the first and second major surfaces 42, 44. Referencing Fig. 6, the major surfaces are substantially flat or planar, i.e., within the limits of manufacturing and material tolerances, and may be preponderantly open or closed, i.e., majority air or fiber, respectively, dependent upon process parameters of belt speed, belt speed differential, type of fiber, vacuum applied, etc.  
15 The loops 48, generally form a succession of "U"-shaped waveforms with the bight 50 of the "U" protruding in the machine, or X axis, direction and midway between the first and second major surfaces 42, 44. The legs 52, 54 of the "U" extend retrograde of the bight 50 towards the major surfaces 42, 44. The loops aggregate in the cross machine direction, or Y axis to form waves or folds running, or extending, in the cross machine direction and being z-  
20 direction oriented to add loft to the nonwoven material. The periodicity of the waveforms may be regular or random and recurrent as seen in Fig. 5 where the loops are alternately more densely 56 and less densely 58 packed along the machine direction. With this embodiment of low density material definite open channels 60 may be seen between the waves.

The fabric of Figs. 4-7 was made using no speed differential between the  
25 moving surfaces 32, 33 and with no vacuum applied to opposite sides of the slot 35.

As seen in Figs. 8-10, a lofty nonwoven material 62 has first major surface 64 which is substantially flat or planar, and a second major surface 66 which is ridged or waved. The fiber loops, e.g., 68 have termini 69 fused into the first major surface 64, but are not fused and therefore protrude in the Z direction at the second major surface 66. The  
30 termini extend retrograde of the loops, e.g., 68, owing to the differential speed of the forming surfaces, or wires 32, 33. The loops aggregate in the cross machine direction to

form serial successive waveforms, collectively 70 as in Fig. 9. In this case the first major surface 64 was formed on the slower moving of the opposing surfaces. If vacuum is differentially applied the first major surface would receive the greater vacuum. In terms of gross morphology, the first major surface 64 is substantially flat and preponderantly closed  
5 in the given example. The waveforms are preponderantly regular in periodicity and length along the cross machine direction. The waves 70 at the second major surface may be crenulate as at 72 depending on the height of slot 35, type of fiber used and other factors. Of course, as stated above, the gross morphology may be easily altered by adjustment of a number of factors within the manufacturing process.

10 While in the foregoing specification this invention has been described in relation to certain preferred embodiments thereof, and many details have been set forth for purpose of illustration, it will be apparent to those skilled in the art that the invention is susceptible to additional embodiments and that certain of the details described herein can be varied considerably without departing from the basic principles of the invention.

15

## WE CLAIM:

1. A lofted web of nonwoven material comprising:  
a plurality of substantially continuous fibers, the web having x, y and z directions, edges, and first and second major surfaces in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;  
the substantially continuous fibers oriented in the z-direction and folded to form loops;  
the first and second major surfaces in the xy planes are spaced apart in the z direction;  
the loops form a waved material with a train of waves spaced along the machine direction, running from edge to edge in the cross direction and extending in the z-direction; and  
the first major surface is flat;  
the second major surface is flat;  
the web is integrally fixed with the waves being substantially "U"-shaped wherein said U-shape has a bight protruding in the machine direction, and, midway between the first major surface and the second major surface, the legs of the "U" extend retrograde of the machine direction towards the first and second major surfaces.
2. The material according to Claim 1 further including the first major surface being substantially open.
3. The material according to Claim 1 further including the first major surface being substantially closed.
4. The material according to Claim 1 further including the second major surface being substantially open.
5. The material according to Claim 1 further including the second major surface being substantially closed.

6. The material according to Claim 1 further including the loops being random.
7. The material according to Claim 1 further including the loops being regular.
8. The material according to Claim 1 further including the waves being random and recurrent.
9. The material according to Claim 1 further including the waves being regular.
10. A lofty material in accordance with Claim 10, wherein said nonwoven web further comprises a composite material having an absorbent.
11. A lofted web of nonwoven material comprising:
  - a plurality of substantially continuous fibers, the web having x, y and z directions, edges, and a first major surface in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;
  - the substantially continuous fibers oriented in the z-direction and folded to form loops;
  - the loops form a waved material with a train of waves spaced along the machine direction running from edge to edge in the cross direction and extending in the z-direction; and
  - the first major surface is flat; and
  - the web is integrally fixed with each wave being a substantially "U"-shaped wherein said U-shape has a bight protruding in the loft direction and the legs of the "U" are spaced along the machine direction and extend towards the first major surface.
12. The material according to Claim 11 further including the waves being oriented off the orthogonal z-axis and uniformly shaped.



13. The material according to Claim 11 further including the waves being oriented off the orthogonal z-axis and crenulate.

14. The material according to Claim 11 further including the first major surface being substantially open.

15. The material according to Claim 11 further including the first major surface being substantially closed.

16. The material according to Claim 11 further including the first major surface being substantially planar.

17. The material according to Claim 11 further including the second major surface being substantially ridged.

18. The material according to Claim 11 further including the loops being random.

19. The material according to Claim 11 further including the loops being regular.

20. The material according to Claim 11 further including the waves being random.

21. The material according to Claim 11 further including the waves being regular.

22. The material according to Claim 11 further including the legs of the "U" extending retrograde towards the first major surface.

23. A lofty material in accordance with Claim 11 further comprising a plurality of staple fibers as a binder.

24. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers comprise an adhesive.

25. A lofty material in accordance with Claim 11, wherein said nonwoven web has a basis weight in a range of about 0.25 osy to about 50 osy.

26. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are polymeric fibers.

27. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are selected from the group consisting of homofilament fibers, bicomponent fibers, biconstituent fibers and combinations thereof.

28. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are thermoplastic fibers.

29. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are crimped.

30. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are substantially linear.

31. A lofty material in accordance with Claim 11, wherein a support structure is attached to at least one face of said nonwoven web.

32. A lofty material in accordance with Claim 11, wherein said nonwoven web further comprises a composite material having an absorbent.

33. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are selected from the group consisting of spunbond, meltblown, and combinations thereof.

34. A lofty material in accordance with Claim 11, wherein said substantially continuous fibers are meltspun.

35. A method for producing a lofty, nonwoven material comprising the steps of:

directing a plurality of substantially continuous fibers into a nip; and  
subjecting said substantially continuous fibers to a vacuum from both sides of said nip, producing a lofty, nonwoven web having z-direction oriented fibers.

36. A method in accordance with Claim 35, wherein the nip is variable.

37. A method in accordance with Claim 35, further including integrally fixing the z-direction orientation of the fibers within the nonwoven material.

38. A method in accordance with Claim 37, wherein the fibers are thermally fixed.

39. A method in accordance with Claim 37, wherein the fibers are adhesively fixed.

40. A method in accordance with Claim 35, wherein the substantially continuous fibers are nonfunctionally bonded.

41. A method in accordance with Claim 35, wherein an adhesive is applied to said plurality of substantially continuous fibers prior to passing through said variable nip.

42. A method in accordance with Claim 35, wherein said variable nip comprises two nip elements having a surface moving at a same linear speed in a machine direction.

43. A method in accordance with Claim 35, wherein said variable nip comprises two nip elements having a surface moving at different linear speeds in a machine direction.

44. A method in accordance with Claim 36, wherein said variable nip comprises a forming belt and a rotating drum.

45. A method in accordance with Claim 35, wherein said plurality of substantially continuous filament fibers are selected from the group consisting of homofilament fibers, bicomponent fibers, biconstituent fibers, and combinations thereof.

46. A method in accordance with Claim 35, wherein said plurality of substantially continuous fibers are selected from the group consisting of spunbond fibers, meltblown fibers and combinations thereof.

47. A method in accordance with Claim 35, wherein said plurality of substantially continuous fibers are deposited onto a support layer, resulting in formation of a laminate.

48. A method in accordance with Claim 35, wherein said plurality of substantially continuous fibers are meltspun fibers.

49. A method for producing a lofty, nonwoven material comprising the steps of:

passing a plurality of substantially continuous fibers through a slot formed by two opposed surfaces whereby said substantially continuous fibers bend from contact with said two opposed surfaces, and fixing the substantially continuous fibers in the bent position, thereby forming a lofty, nonwoven web having a plurality of as-formed z-direction fibers.

50. A method in accordance with Claim 49, wherein said slot is vertically oriented.

51. A method in accordance with Claim 49, wherein said slot is formed between two foraminous wires.

52. A method in accordance with Claim 51, wherein said wires are moving.

53. A method in accordance with Claim 49, further comprising integrally fixing the z-direction of the fibers with heat.

54. A method in accordance with Claim 49, further comprising integrally fixing the z-direction of the fibers with adhesive.

55. A method in accordance with Claim 49, wherein the substantially continuous fibers are nonfunctionally bonded before passing through the slot.

56. A method in accordance with Claim 49 further comprising changing a width of said slot, whereby a density of said nonwoven web is changed.

57. A method in accordance with Claim 49 further comprising adjusting a speed at which said substantially continuous fibers pass through said slot, whereby a density of said nonwoven web is changed.

58. A method in accordance with Claim 52 further comprising moving the wires at a differential speed to produce a ridged surface on the nonwoven web.

59. A method in accordance with Claim 49, wherein said substantially continuous fibers are selected from the group consisting of spunbond fibers, meltblown fibers and combinations thereof.

60. A method in accordance with Claim 49, wherein a support material is applied to at least one face of said nonwoven web, forming a laminate.

61. A personal care absorbent article comprising:  
a nonwoven web comprising a plurality of substantially continuous fibers oriented in a z-direction of said nonwoven web.

62. A personal care absorbent article in accordance with Claim 61, wherein said nonwoven web further comprises an absorbent.

63. A filtration material comprising:  
a nonwoven web comprising a plurality of substantially continuous fibers oriented in a z-direction of said nonwoven web.

64. A filtration material in accordance with Claim 63, wherein said substantially continuous fibers are crimped.

65. A surgical garment comprising:  
a nonwoven web comprising a plurality of substantially continuous fibers oriented in a z-direction of said nonwoven web.




FIG. 1






FIG. 2



**FIG. 3A**  
PRIOR ART



**FIG. 3B**

SUBSTITUTE SHEET (RULE 26)






FIG. 4




FIG. 5






FIG. 6





FIG. 7






FIG. 8




FIG. 9



FIG. 10

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/10759

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 D04H3/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 D04H A61F B65H A44B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)  
EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 2 063 321 A (TOA NENRYO KOGYO K.K.) 3 June 1981 (1981-06-03)  the whole document	1-9, 49, 51, 52, 55, 56, 59
X	US 3 738 884 A (SOEHNGEN, HEIGHTS) 12 June 1973 (1973-06-12) column 5, line 69 -column 6, line 13; figures 1,4-7	1-9, 49, 55, 63
X	GB 2 267 100 A (KABUSHIKI KAISHA RISURON) 24 November 1993 (1993-11-24)  page 1, line 21 -page 2, line 14 page 12, line 18 -page 13, line 8; figures 1,7,8	11-14, 16-18, 20, 26-28, 30

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*G\* document member of the same patent family

Date of the actual completion of the international search

22 August 2000

Date of mailing of the international search report

30/08/2000

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Seabra, L

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 00/10759

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>EP 0 765 616 A (JAPAN VILENE COMPANY LTD) 2 April 1997 (1997-04-02)</p> <p>column 1, line 47-59 column 3, line 4-15; figures 1,2,4,6,7</p>	11, 13-18, 20, 25-28, 30,31
X	<p>EP 0 137 644 A (PERSONAL PRODUCTS COMPANY) 17 April 1985 (1985-04-17)</p> <p>page 1, line 5-13 page 13, line 22 -page 14, line 5 page 17, line 28 -page 18, line 18; figures 3A,7</p>	11,12, 14-21, 23-28, 30-34, 49,53, 54,59, 61,62
A	<p>US 4 111 733 A (GILBERT PERIERS) 5 September 1978 (1978-09-05) column 3, line 41 -column 4, line 27; figure 1</p>	49,53,54
X	<p>US 5 702 801 A (JUNG-FU CHIEN) 30 December 1997 (1997-12-30) column 5, line 44-67 column 8, line 36-65; figures 2-10,27</p>	49,50, 53,60,63
X	<p>US 5 500 295 A (HALM, JONES, KIRKBRIDE, MARCUS, SNYDER) 19 March 1996 (1996-03-19) column 5, line 26 -column 7, line 35; figures 5,6</p>	49,50, 55,59
X	<p>US 5 270 107 A (SCOTT GESSNER) 14 December 1993 (1993-12-14) column 1, line 6-19 column 6, line 35-51</p>	61-65

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/10759

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2063321	A	03-06-1981	JP 1010618 B	22-02-1989
			JP 1540502 C	31-01-1990
			JP 56068152 A	08-06-1981
			BE 885979 A	30-04-1981
			CA 1160010 A	10-01-1984
			CH 650039 A	28-06-1985
			DE 3041089 A	21-05-1981
			FR 2468675 A	08-05-1981
			US 4409282 A	11-10-1983
US 3738884	A	12-06-1973	US 3607588 A	11-05-1971
			US 3740302 A	19-06-1973
			US 3749633 A	31-07-1973
GB 2267100	A	24-11-1993	JP 3057537 B	26-06-2000
			JP 5311561 A	22-11-1993
EP 0765616	A	02-04-1997	US 5786060 A	28-07-1998
EP 0137644	A	17-04-1985	US 4578070 A	25-03-1986
			AT 55238 T	15-08-1990
			AU 565232 B	10-09-1987
			AU 3190284 A	21-02-1985
			BR 8404038 A	16-07-1985
			CA 1226120 A	01-09-1987
			DE 3482928 D	13-09-1990
			DK 390084 A	16-02-1985
			FI 843203 A,B,	16-02-1985
			GB 2145126 A,B	20-03-1985
			GR 79970 A	31-10-1984
			HK 99386 A	24-12-1986
			IE 55605 B	21-11-1990
			JP 2096329 C	02-10-1996
			JP 7121270 B	25-12-1995
			JP 60052603 A	25-03-1985
			KR 9103223 B	24-05-1991
			MX 172130 B	06-12-1993
			MY 28987 A	31-12-1987
			NO 843242 A,B,	18-02-1985
			NZ 209139 A	30-10-1987
			NZ 221338 A	28-10-1988
			PH 22505 A	12-09-1988
			PT 79069 A,B	01-09-1984
			SG 75586 G	27-02-1987
			ZA 8406312 A	26-03-1986
			CA 1253320 A	02-05-1989
			MX 161113 A	31-07-1990
			CA 1253319 A	02-05-1989
US 4111733	A	05-09-1978	NONE	
US 5702801	A	30-12-1997	US 5558924 A	24-09-1996
			DE 69312763 D	11-09-1997
			DE 69312763 T	12-03-1998
			EP 0558205 A	01-09-1993
			ES 2109431 T	16-01-1998
US 5500295	A	19-03-1996	US 5338500 A	16-08-1994

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. tional Application No

PCT/US 00/10759

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5500295 A		US 5238612 A	24-08-1993
		US 5112684 A	12-05-1992
		US 4940502 A	10-07-1990
		US 4794038 A	27-12-1988
		US 4618531 A	21-10-1986
		US 5344707 A	06-09-1994
		AU 7654091 A	11-11-1991
		CA 2080363 A	13-10-1991
		CN 1056849 A,B	11-12-1991
		DE 69105269 D	05-01-1995
		DE 69105269 T	11-05-1995
		EP 0524240 A	27-01-1993
		ES 2065022 T	01-02-1995
		NZ 237772 A	25-11-1993
		PT 97343 A	31-08-1993
		WO 9116485 A	31-10-1991
		US 5218740 A	15-06-1993
		AU 7680291 A	11-11-1991
		CA 2079225 A	13-10-1991
		CN 1058818 A,B	19-02-1992
		DE 69105966 D	26-01-1995
		DE 69105966 T	24-05-1995
		EP 0524221 A	27-01-1993
		ES 2067226 T	16-03-1995
		PT 97344 A	30-07-1993
		WO 9116484 A	31-10-1991
		AU 8283691 A	04-02-1992
		CA 2086840 A	10-01-1992
		DE 69111608 D	31-08-1995
		DE 69111608 T	21-03-1996
		EP 0538372 A	28-04-1993
		ES 2076539 T	01-11-1995
		JP 3012327 B	21-02-2000
		KR 158667 B	01-12-1998
		MX 9100124 A	28-02-1992
		WO 9201104 A	23-01-1992
		US 5169580 A	08-12-1992
		US 5294392 A	15-03-1994
		AT 72680 T	15-03-1992
		AU 629277 B	01-10-1992
		AU 4707489 A	05-07-1990
		BR 8906745 A	18-09-1990
		CA 2006207 A,C	27-06-1990
		DE 68900841 D	26-03-1992
		DK 660989 A	28-06-1990
		EP 0378001 A	18-07-1990
		ES 2030274 T	16-10-1992
		JP 1986142 C	08-11-1995
		JP 2221451 A	04-09-1990
US 5270107 A	14-12-1993	AU 4044693 A	18-11-1993
		MX 9302245 A	31-08-1994
		WO 9321371 A	28-10-1993





(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
9 November 2000 (09.11.2000)

PCT

(10) International Publication Number  
**WO 00/66824 A1**

(51) International Patent Classification<sup>7</sup>: **D04H 3/16**

Richard, Wallace; 8048 West Arapaho Court, Boise, ID 83703 (US).

(21) International Application Number: PCT/US00/10759

(22) International Filing Date: 21 April 2000 (21.04.2000)

(74) Agents: NORRIS, Roland, W.; Pauley Petersen Kinne & Fejer, Suite 365, 2800 West Higgins Road, Hoffman Estates, IL 60195 et al. (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/132,031 30 April 1999 (30.04.1999) US  
09/537,564 30 March 2000 (30.03.2000) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(71) Applicant: **KIMBERLY-CLARK WORLDWIDE, INC.** [US/US]; 401 North Lake Street, Neenah, WI 54956 (US).


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors: NEELY, James, Richard; 3585 Waters Cove Way, Alpharetta, GA 30202 (US). WHITE, Edward, Jason; 12206 Aroniminik Point, Knoxville, TN 37922 (US). BROWN, Kurtis, Lee; 700 Rhodes Creek Trail, Alpharetta, GA 30004 (US). CONRAD, John, Herbert; 625 Briars Bend, Alpharetta, GA 30004 (US). HOEFER,

Published:  
— With international search report.

[Continued on next page]

(54) Title: CONTROLLED LOFT AND DENSITY NONWOVEN WEBS AND METHOD FOR PRODUCING



WO 00/66824 A1

(57) Abstract: A lofty, nonwoven material having a nonwoven web having a plurality of substantially continuous fibers oriented in a z-direction of the nonwoven web and a method for producing the lofty, nonwoven material from as-formed z-direction fibers. The method is fast, having no mechanical manipulation of the fibers to slow it down, easily adjustable and allows for in-line processing. The material can be varied from preponderantly open to preponderantly closed in its web structure.



— *With amended claims and statement.*

**Date of publication of the amended claims and statement:**  
21 December 2000

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

## AMENDED CLAIMS

[received by the International Bureau on 25 October 2000 (25.10.00);  
original claims 1, 49, 61, 63 and 65 amended;  
original claims 10 and 50 cancelled;  
remaining claims unchanged (6 pages)]

1. A lofted web of nonwoven material comprising:  
a plurality of substantially continuous fibers, the web having x, y and z directions, edges, and first and second major surfaces in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;  
the substantially continuous fibers oriented in the z-direction and folded to form loops;  
the first and second major surfaces in the xy planes are spaced apart in the z direction;  
the loops form a waved material with a train of waves spaced along the machine direction, running from edge to edge in the cross direction and extending in the z-direction; and  
the first major surface is flat;  
the second major surface is flat;  
the web is integrally fixed with the waves being substantially "U"-shaped wherein said U-shape has a bight protruding in the machine direction, and, midway between the first major surface and the second major surface, the legs of the "U" extend retrograde of the machine direction towards the first and second major surfaces; and  
wherein said nonwoven web further comprises a composite material having an absorbent.

2. The material according to Claim 1 further including the first major surface being substantially open.

3. The material according to Claim 1 further including the first major surface being substantially closed.

4. The material according to Claim 1 further including the second major surface being substantially open.

5. The material according to Claim 1 further including the second major surface being substantially closed.

6. The material according to Claim 1 further including the loops being random.

7. The material according to Claim 1 further including the loops being regular.

8. The material according to Claim 1 further including the waves being random and recurrent.

9. The material according to Claim 1 further including the waves being regular.

11. A lofted web of nonwoven material comprising:

a plurality of substantially continuous fibers, the web having x, y and z directions, edges, and a first major surface in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;

the substantially continuous fibers oriented in the z-direction and folded to form loops;

the loops form a waved material with a train of waves spaced along the machine direction running from edge to edge in the cross direction and extending in the z-direction; and

the first major surface is flat; and

the web is integrally fixed with each wave being a substantially "U"-shaped wherein said U-shape has a bight protruding in the loft direction and the legs of the "U" are spaced along the machine direction and extend towards the first major surface.

12. The material according to Claim 11 further including the waves being oriented off the orthogonal z-axis and uniformly shaped.

49. A method for producing a lofty, nonwoven material comprising the steps of:

passing a plurality of substantially continuous fibers through a slot formed by two opposed surfaces whereby said substantially continuous fibers bend from contact with said two opposed surfaces, and fixing the substantially continuous fibers in the bent position, thereby forming a lofty, nonwoven web having a plurality of as-formed z-direction fibers; and

wherein said slot is vertically oriented.

51. A method in accordance with Claim 49, wherein said slot is formed between two foraminous wires.

52. A method in accordance with Claim 51, wherein said wires are moving.

53. A method in accordance with Claim 49, further comprising integrally fixing the z-direction of the fibers with heat.

54. A method in accordance with Claim 49, further comprising integrally fixing the z-direction of the fibers with adhesive.

55. A method in accordance with Claim 49, wherein the substantially continuous fibers are nonfunctionally bonded before passing through the slot.

56. A method in accordance with Claim 49 further comprising changing a width of said slot, whereby a density of said nonwoven web is changed.

57. A method in accordance with Claim 49 further comprising adjusting a speed at which said substantially continuous fibers pass through said slot, whereby a density of said nonwoven web is changed.

58. A method in accordance with Claim 52 further comprising moving the wires at a differential speed to produce a ridged surface on the nonwoven web.

59. A method in accordance with Claim 49, wherein said substantially continuous fibers are selected from the group consisting of spunbond fibers, meltblown fibers and combinations thereof.

60. A method in accordance with Claim 49, wherein a support material is applied to at least one face of said nonwoven web, forming a laminate.

61. A personal care absorbent article comprising:  
a nonwoven web comprising a plurality of substantially continuous fibers;  
the web having x, y and z directions, edges, and a first major surface in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;  
the substantially continuous fibers oriented in the z-direction and folded to form loops;  
the loops form a waved material with a train of waves spaced along the machine direction running from edge to edge in the cross direction and extending in the z-direction; and  
the first major surface is flat; and  
the web is integrally fixed with each wave being a substantially "U"-shaped wherein said U-shape has a bight protruding in the loft direction and the legs of the "U" are spaced along the machine direction and extend towards the first major surface.

62. A personal care absorbent article in accordance with Claim 61, wherein said nonwoven web further comprises an absorbent.

63. A filtration material comprising:

a nonwoven web comprising a plurality of substantially continuous fibers;  
the web having x, y and z directions, edges, and a first major surface in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;

the substantially continuous fibers oriented in the z-direction and folded to form loops;

the loops form a waved material with a train of waves spaced along the machine direction running from edge to edge in the cross direction and extending in the z-direction; and

the first major surface is flat; and

the web is integrally fixed with each wave being a substantially "U"-shaped wherein said U-shape has a bight protruding in the loft direction and the legs of the "U" are spaced along the machine direction and extend towards the first major surface.

64. A filtration material in accordance with Claim 63, wherein said substantially continuous fibers are crimped.

65. A surgical garment comprising:

a nonwoven web comprising a plurality of substantially continuous fibers;  
the web having x, y and z directions, edges, and a first major surface in an x-y plane, with x being a machine direction, y being a cross machine direction and z being a loft direction;

the substantially continuous fibers oriented in the z-direction and folded to form loops;

the loops form a waved material with a train of waves spaced along the machine direction running from edge to edge in the cross direction and extending in the z-direction; and

the first major surface is flat; and

the web is integrally fixed with each wave being a substantially "U"-shaped wherein said U-shape has a bight protruding in the loft direction and the legs of the "U" are spaced along the machine direction and extend towards the first major surface.



**STATEMENT UNDER ARTICLE 19**

Claim 1 of the subject application has been amended to incorporate Claim 10 which claims a lofted nonwoven web further comprising a composite material having an absorbent.

Claim 10 has been deleted.

Claim 49 has been amended to incorporate Claim 50 which references the slot as being vertically oriented.

Claim 50 has been deleted.

Claims 61, 63 and 65 have been narrowed by adding the limitations to better define the Z-direction web.

Replacement pages 13-14 and 19, 20, 20.1 and 20.2 are enclosed.

No new matter has been added to this application.

